



BRICKFORM® Antique Release™

WWW.TUCKER.COM

CALL: 330.928.2155

Colored Bond-Breaker

BRICKFORM Antique Release is a colored powder that forms a waterproof barrier and reduces concrete build-up on BRICKFORM Texture Mats™. Available in 40 standard colors, BRICKFORM Antique Release can also be custom-matched to almost any color. Use BRICKFORM Antique Release and BRICKFORM Texture Mats over BRICKFORM Color Hardener™ to create the look and feel of many natural materials.

FEATURES

- Prevents Concrete Buildup
- Prolongs Tool Life
- Fade-Resistant
- Unlimited Effects & Color Combinations



PRODUCT DESCRIPTION • Made with the finest ultra-violet-resistant pigments available, BRICKFORM Antique Release stands up to the effects of sunlight. BRICKFORM Antique Release is made from a finely ground formula that works with polyurethane, texturing mats to create a beautifully antiqued and textured concrete surface.

USES • BRICKFORM Antique Release is broadcast onto the concrete surface, prior to the placement of mat-type texturing tools or rollers. The release prevents the concrete from adhering to the texturing mats. A portion of the release becomes imbedded into the concrete, usually where there is relief in the texturing tool, leaving behind an antiqued appearance. BRICKFORM Antique Release can be used in matching or contrasting colors to create a variety of effects. A combination of colors can add interesting shadings and highlights to the finished concrete surface.

LIMITATIONS • BRICKFORM Antique Release should not be used as the primary coloring agent. It should be applied over freshly placed, still plastic, color-hardened or integrally colored concrete surfaces.

COLORS • BRICKFORM Antique Release is available in 40 standard colors to match or contrast with BRICKFORM Color Hardener. Custom colors and color matching are also available.

PACKAGING • BRICKFORM Antique Release is packaged in convenient 30-pound (13.5 kg), moisture-resistant, plastic pails.

COVERAGE • The rate of application for BRICKFORM Antique Release will vary depending upon the depth of the texturing-mat impressions, the degree to which the concrete has been set, and the intensity of the contrast desired. Generally, 3.5 pounds (1.57 kg) or more per 100 square feet (9.29 m²) is required.

STORAGE • Store in a cool, dry place, away from acids and strong oxidants. Do not store in temperatures exceeding 120°F (48.8°C). Keep containers tightly sealed. Shelf life is approximately three years if package remains sealed in the original plastic bucket and is not opened, cracked, damaged or subjected to extreme conditions. **Note** – pigment colors may drift over a period of time, BRICKFORM recommends using same lot numbers OR mixing buckets of the same color from different lot numbers.

CAUTION • KEEP OUT OF REACH OF CHILDREN. Before using or handling, read the Material Safety Data Sheet and Warranty. DO NOT TAKE INTERNALLY. All concrete finishers and all onsite personnel must wear an OSHA-NIOSH approved dust respirator while applying or working around this product. Avoid contact with skin and eyes. Wear rubber gloves to protect skin and safety eye goggles. Close containers after each use. Use good hygiene when handling this product and wash and bathe after each use. Be sure to wash clothing after each use.

PREPARATION • BRICKFORM strongly recommends representative jobsite samples. Individuals who will be performing the work should use the specified materials, as well as the finishing and curing techniques that will be used on the project. Before applying BRICKFORM Antique

Release, protect all surrounding areas to reduce the possibility of staining during application and removal. BRICKFORM Antique Release may be applied to the surface of the freshly placed concrete as soon as all standing water has disappeared from the concrete surface. Typically, concrete has, at least, a fresno finish. However, if BRICKFORM Color Hardener has been applied, the finishing will be more extensive.

APPLICATION • Apply in temperatures between 55° and 80°F (12.8°C and 26.7°C). BRICKFORM Antique Release should be broadcast by hand or with the use of a 6" mason's brush until a thin, uniform layer covers the concrete surface to be textured. BRICKFORM Antique Release should not be broadcast for more than a few feet or from above the knee. Avoid windy conditions. Over-application will decrease detail of the texture. Do NOT trowel the material into the concrete. Application of texturing mats may begin as soon as the release agent has been applied. BRICKFORM Antique Release should be removed from the concrete surface when removal can be safely accomplished, without any damage to the curing, concrete surface. Excess release agent may be swept from the slab. Residual BRICKFORM Antique Release may be removed to the degree desired by pressure-washing after 48-72 hours. Care must be taken not to damage the curing, colored-concrete surface. The amount of BRICKFORM Antique Release adhering to the concrete surface will depend upon how hard the concrete surface was at the time of application and texturing. A softer surface will retain more release agent than a harder concrete surface. If too much Antique Release remains on the surface after rensing, use BRICKFORM Neutra Clean™ following the Neutra Clean Technical Information Sheet.

SEALING • After the concrete has been allowed to cure for 28 days, protect the surface with BRICKFORM Gem-Seal, Poly-Astic, Poly-Seal, Safety-Seal, or Satin-Seal. Please get a copy of the appropriate Technical Information and Material Safety Data Sheet before attempting to use these products. Once sealed, protect the surface from foot traffic for 24 hours and vehicular traffic for 5 days.

MAINTENANCE • The sealed surface should be inspected periodically for areas of thin or traffic-worn sealer. Brickform recommends the application of Dura-Wax as a sacrificial coating on interior surfaces. Reapply as needed, according to the appropriate Technical Information Sheet. If traces of efflorescence are present, this should first be eliminated with a gentle cleaner such as BRICKFORM E-Etch, according to the BRICKFORM E-Etch Technical Information Sheet.

WARRANTY • This product is not intended for public use and is intended for use by licensed contractors and installers, experienced and trained in the use of these products. It is warranted to be of uniform quality, within manufacturing tolerances. The manufacturer has no control over the use of this product, therefore, no warranty, expressed or implied, is or can be made either as to the effects or results of such use. In any case, the manufacturer's obligations shall be limited to refunding the purchase price or replacing material proven defective. The end user shall be responsible for determining product's suitability and assumes all risks and liability.

PLAN SPECIFICATION

BRICKFORM® Antique Release™ Suggested Short Form Specification: All concrete flatwork designated in the plans and specifications as imprinted with an antiquing release agent shall be color hardened with BRICKFORM Color Hardener™, in accordance with the *BRICKFORM Color Hardener Technical Information Sheet*, using _____ color and a minimum of _____ lbs. Per 100 square feet (_____ kg per _____ 9.29 m²). Color hardened surface shall then be released and imprinted with BRICKFORM Antique Release™ in accordance with the *BRICKFORM Antique Release Technical Information Sheet*, using _____ color at _____ lbs. per 100 square feet (_____ kg per _____ m²). After the concrete has been allowed to cure for 28 days, all colored and antiqued surfaces shall be sealed with BRICKFORM Gem-Seal™, Poly-Seal™, BRICKFORM Safety-Seal™, or BRICKFORM Satin-Seal™ in accordance to the corresponding Technical information Sheet. All products shall be manufactured by BRICKFORM, 800-483-9628, Rancho Cucamonga, CA 909-484-3399. BRICKFORM Color Hardener meets ASTM STDS – abrasion resistance and PSI.

ORDER SPECIFICATIONS

Product

Antique Release

Shipping Weight: Container Size:

31.0 lbs (13.95 kg)

5-Gallon (18.92 L) Buckets

Item No. Color

RA-100 Dark Gray
RA-115 Venetian Pink
RA-200 Medium Gray
RA-250 Oyster White
RA-300 Nutmeg
RA-310 Cream Beige
RA-320 Golden Sandstone
RA-325 Sandstone
RA-330 Coconut
RA-350 Desert Tan
RA-375 Buff Tan
RA-400 Chestnut
RA-425 Autumn Brown
RA-500 Tile Red
RA-515 Sunbaked Clay
RA-525 Dusty Rose
RA-550 Brick Red
RA-575 Victorian Red
RA-600 Light Gray
RA-615 Stone Gray
RA-625 Dover Blue

Item No. Color

RA-650 Smokey Blue
RA-700 Terra Cotta
RA-735 Cappuccino
RA-810 Walnut
RA-815 French Gray
RA-825 Slate Green
RA-900 Black
RA-1000 White
RA-1010 Smokey Beige
RA-1015 Blush Beige
RA-1020 Antique Rose
RA-1030 Ash White
RA-1035 Summer Beige
RA-1040 Weathered Sage
RA-1045 Shadow Slate
RA-1050 Antique Cork
RA-1055 Pecos Sand
RA-1065 Quarry Red
RA-1070 Sandy Buff
RA-1080 Adobe Buff
RA-1090 Sun Buff