

Protectosil® CHEM-TRETE® PB VOC

WATER REPELLENT

Product Data and Test Information

PRODUCT NAME

Protectosil® CHEM-TRETE® PB VOC

High-performance, penetrating water repellent for porous substrates.

MANUFACTURER

Evonik Degussa Corporation
379 Interpace Parkway, P.O. Box 677
Parsippany, NJ 07054-0677
1 (800) 828-0919
info.protectosil@evonik.com
www.protectosil.com

PROTECTOSIL PRODUCTS ARE MANUFACTURED AT THE EVONIK DEGUSSA CORPORATION THEODORE, ALABAMA, PLANT UNDER A QUALITY SYSTEM CERTIFIED TO ISO-9001 AND ISO-14001 REQUIREMENTS.

PRODUCT DESCRIPTION

A clear, penetrating, breathable water repellent for use on concrete, brick, concrete masonry units and some natural stones. Prevents water and waterborne contaminants from entering the substrate and causing premature deterioration. Penetrates into the substrate and chemically bonds with silica to form a permanent attachment of the water repellent molecule. **Protectosil CHEM-TRETE PB VOC** is especially suited for making porous substrates such as split-face block water repellent. This water repellent effect stands up against wind-driven rain.

By preventing water and waterborne contaminants from entering the substrate, **Protectosil CHEM-TRETE PB VOC** reduces problems such as efflorescence, leaching, acid rain deterioration, scaling, dirt buildup, staining, corrosion of reinforcing steel and mildew. **Protectosil CHEM-TRETE PB VOC** will not cause adverse surface appearance of the substrate. Treated surfaces are fully breathable because the natural moisture vapor transmission is not affected. This will eliminate problems caused by entrapped moisture, including blushing of the sealer and freeze-thaw damage to the masonry.

APPROPRIATE APPLICATIONS

Materials such as concrete masonry units (split-face, fluted or ground-faced blocks) can be protected from the ingress of wind-driven rain.

Brick masonry, especially single-wythe wall construction, can be treated to prevent moisture from entering and damaging interior walls.

Provides resistance against water and waterborne contaminants to reduce staining.

Other substrates that can be protected include sandstone, terra-cotta, hand-molded bricks and natural stones.

ADVANTAGES

Protectosil CHEM-TRETE PB VOC is a proprietary mixture of alkyltrialkoxysilanes in a special carrier system. The **Protectosil CHEM-TRETE PB VOC** is designed to provide a high level of surface beading with penetration, to protect against wind-driven rain. The silane components are unique because they chemically bond to the silica in the substrate and set up a hydrophobic layer of protection. Because of the silane's unique chemistry, a long service life is possible. By incorporating **Protectosil CHEM-TRETE PB VOC** into your integrated design, you can earn vital Leadership in Energy & Environmental Design (LEED) credits for both new and existing construction projects.

The main benefits of the product are:

- Excellent resistance to wind-driven rain
- Excellent resistance to chloride ion ingress
- Reduced efflorescence
- Breathable system
- Penetration into the substrate
- Long service life
- No blushing, peeling or yellowing
- Resistance to alkali attack
- Keeps substrate cleaner

LIMITATIONS

Not intended for below-grade waterproofing. Will leave a residue on nonporous materials such as glass, metal and painted surfaces. Asphalt-based materials such as roofing materials and plastic products, shrubbery, and plant life should be protected from overspray.

Should not be applied if the surface temperature is below 20°F (-7°C) or above 100°F (40°C), if rain is expected within 4 hours following application, or if high winds or other conditions prevent proper application. If rain has preceded the application, the surface should be allowed to dry for at least 48 hours.

(Continued)

TECHNICAL DATA

Protectosil CHEM-TRETE PB VOC is a clear, colorless liquid composed of alkyltrialkoxysilanes with activator in denatured alcohol.

Color	water white
Active Substance	alkyltrialkoxysilane
Active Content	>40%
Solvent	denatured ethyl alcohol
Flash Point	54°F
Density	6.7 lb/gal
VOC	580 g/l

TEST DATA

ASTM C 140 "Sampling and Testing Concrete Masonry Units, Absorption"

24-hour submersion test – 99.4% effective in reducing water intrusion

ASTM C 67 "Sampling and Testing Brick and Structural Clay Tile, Part 7 Absorption"

24-hour submersion test – 99.8% effective in reducing moisture intrusion

ASTM C 642 "Specific Gravity, Absorption and Voids in Hardened Concrete"

24-hour immersion – 97.5% effective

ASTM D 1653 "Moisture Vapor Permeability of Organic Coatings"

68 g/ft²/24 hours – 97% breathability

ASTM E 514 "Water Permeance of Masonry"
Concrete Block Wall

Untreated leakage	6.47	l/hr
Treated leakage	0	l/hr
Reduction in leakage	100%	

Brick Wall

Untreated leakage	1.00	l/hr
Treated leakage	0	l/hr
Reduction in leakage	100%	

INSTALLATION

Concrete must be allowed to cure for a minimum of 28 days. All repointing must be completed and allowed to cure for at least 3 days. Concrete repair and replacement must be completed prior to application of **Protectosil CHEM-TRETE PB VOC**. Patching materials, caulking, sealing materials and traffic paint must be fully cured before applying **Protectosil CHEM-TRETE PB VOC**.

All surfaces must be cleaned to remove all traces of dirt, dust, efflorescence, mold, salt, grease, oil, asphalt, laitance, curing compounds, paint, coatings and other foreign materials. Acceptable surface cleaning methods include shotblasting,

sandblasting, waterblasting and using chemical cleaners. Check with your Protectosil representative to verify that surface preparation is adequate.

Protectosil CHEM-TRETE PB VOC should be applied using low-pressure (15 to 25 psi) pumping equipment with a wet fan type spray nozzle. Alternate methods include using either a power roller with a 1" nap or a brush. Do not alter or dilute the material. Do not apply to a wet or damp substrate. A test patch should be applied to the substrate to verify coverage rate, application conditions and desired results.

On vertical surfaces, apply the **Protectosil CHEM-TRETE PB VOC** in a flooding application from the bottom up, so the material runs down 6 to 8 inches below the spray pattern. On horizontal surfaces, the liquid material should pond on the surface for at least 5 seconds before being absorbed. Coverage rates on vertical surfaces depend on the type of material to be treated. Typical application rates are from 50 to 125 ft²/gal. Your Protectosil representative can give an exact coverage rate for your particular project.

Protect glass, metal, plastic, asphalt materials and nonporous substrates from overspray. **Protectosil CHEM-TRETE PB VOC** will not etch glass but will leave a residue on nonporous surfaces. Check that pump equipment is clean and has no water in lines, nozzles or pump. Please refer to the "**Protectosil CHEM-TRETE PB VOC** Application Instructions" for more detailed information.

Precautions: Protectosil CHEM-TRETE PB VOC is a flammable liquid and should be kept away from heat, sparks, open flame and other sources of ignition. **Protectosil CHEM-TRETE PB VOC** containers should be kept closed when not in use and should be stored at temperatures between 0°F (-18°C) and 120°F (50°C), away from rain and standing water. When working in an enclosed area, an air respirator should be used. Please refer to material safety data sheet for more detailed information.

AVAILABILITY

Protectosil CHEM-TRETE PB VOC is available in 5- and 55-gallon drums through authorized distributors throughout the United States and Canada. Contact Evonik Degussa Corporation at 1 (800) 828-0919 for the sales representative in your area to get specific cost information.

TECHNICAL SERVICE

Technical service engineers and chemists are available to answer questions about product performance, application methods and compatibility with other building materials.

For more information, MSDS and the most updated product information, and to find your local representative, go to www.protectosil.com.

Protectosil®, **CHEM-TRETE®** = registered trademarks of Evonik GmbH.

This information and all technical and other advice are based on Evonik Degussa Corp's ("Evonik") present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility and obligation to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.