



**WEATHERPROOF™**  
**Foundation Coating-Brush Grade**  
**#41305**

A liquid applied coating manufactured from specially prepared asphalt and solvents. Designed for application to below grade concrete, masonry and metal surfaces for dampproofing. Applied as directed, it forms a smooth, tough film which helps to retard the entrance of moisture into or through the foundation wall.

**Uses**

Below grade dampproofing for concrete, masonry or metal surfaces.

**Advantages**

- Can be brushed or spray applied.
- Economical.
- Stays pliable.

**INSTALLATION**

**Coverage**

- Product yield to achieve desired rate will be from 1 to 1.5 gallons per 100 square feet per coat. The yield varies according to the existing surface texture. As a general rule, the smoother the surface, the less material is required.
- Recommended application rate per coat is 16 to 24 mils wet film thickness which will produce 10 to 16 mils dry. A mil is 1/1000 of an inch.

**Surface Preparation**

Remove all loose materials, dirt and dust from surface to be coated. Heavy deposits and stains should be wire brushed. Make certain that surface is dry.

**Application**

- Apply by spray with pump and gun sized by a knowledgeable pump dealer for the particular application or by roofing brush or roller. Allow 24 to 48 hours before applying second coat depending upon weather.
- Clean up with mineral spirits, but do not thin the product with this or any other solvents.
- If the product is difficult to spread in cooler temperatures, warm containers by storing them overnight in room at 65° to 75° F.

### **Drying Time**

- Four hours to touch at 70° F. & 50% relative humidity per coat. Twenty-four to 48 hours is required for thorough evaporation of solvent. Cool or overcast weather slows drying. Hot, dry weather with strong air circulation provides optimum drying conditions. (See Restrictions.)

### **Restrictions**

- Do not use with PVC film.
- Do not use where material, once applied, may come into contact with potable water.
- Surfaces to be coated must be dry and clean and must remain so for 24 to 48 hours after application for each coat.
- Do not backfill until product has dried thoroughly.
- Do not use on wood.
- For exterior use only.

### **Cautions**

This product is combustible. Keep away from heat, sparks and open flame. Avoid repeated or prolonged contact with skin. If swallowed, do not induce vomiting. Contact Physician immediately. Keep container closed when not in use. **KEEP AWAY FROM CHILDREN.** Product label and Material Safety Data Sheet contain further information on the safe use of this product and precautions for the safe disposal of the container. They should be read and understood prior to use.

## **SPECIFICATIONS**

|   |                     |
|---|---------------------|
| Percent Solids by Weight .....              | 80%                 |
| Percent Solids by Volume.....               | 75%                 |
| Weight Per Gallon: Pounds .....             | 8                   |
| Flash Point minimum .....                   | 105° F. (Seta C.C.) |
| P.H. ....                                   | N/A                 |
| Viscosity at 77° F. ....                    | 800 cps.            |
| Mildew Resistance: .....                    | Good                |
| Water Resistance: Intermittent Exposure.... | Good                |
| Water Resistance: Continuous Immersion .    | Poor                |
| VOC . ....                                  | <250 grams/liter    |

## **PACKAGING INFORMATION**

| <b><u>Product Number</u></b> | <b><u>Size</u></b> | <b><u>Quantity</u></b> | <b><u>Weight</u></b> |
|------------------------------|--------------------|------------------------|----------------------|
| 41355                        | 55 Gal.            | Each                   | 490 lbs.             |
| 41305                        | 5 Gal.             | Each                   | 41 lbs.              |
| 41301                        | 1 Gal.             | Case of 4              | 40 lbs.              |